

CLAIMS:

1. A dielectric paste adapted for forming a spacer layer and containing an acrylic system resin as a binder and at least one solvent selected from a group consisting of limonene, α -terpinyl acetate, I-dihydrocarvyl acetate, I-menthone, I-perillyl acetate, I-carvyl acetate, and d- dihydrocarvyl acetate as a solvent.
5
2. A dielectric paste adapted for forming a spacer layer in accordance with Claim 1, wherein the weight-average molecular weight of the acrylic system resin is equal to or larger than 450,000 and equal to or smaller than 900,000.
10
3. A dielectric paste adapted for forming a spacer layer in accordance with Claim 1, wherein the acid value of the acrylic system resin is equal to or larger than 5 mgKOH/g and equal to or smaller than 25 mgKOH/g.
15
4. A dielectric paste adapted for forming a spacer layer in accordance with Claim 2, wherein the acid value of the acrylic system resin is equal to or larger than 5 mgKOH/g and equal to or smaller than 25 mgKOH/g.

20